

# Tufchem™ Novolac Sprayable Epoxy

## SELECTION & SPECIFICATION DATA

<b>Type</b>	High functional novolac epoxy lining
<b>Description</b>	Tufchem Novolac Sprayable Epoxy is a nominal 1/8" (3 mm) thick high functional novolac epoxy lining system for high corrosion applications. It is applied with specialty peristaltic pump equipment by contractors familiar with the use of such equipment.
<b>Uses</b>	<ul style="list-style-type: none"> <li>• Resistant to most acids, alkalis and aliphatic solvents.</li> <li>• Suitable for wastewater collection and treatment containment areas</li> <li>• Basins, manholes, junction boxes</li> <li>• Secondary containment</li> <li>• Floors, walls, curbs, ceilings</li> </ul>
<b>Features</b>	<ul style="list-style-type: none"> <li>• Spray application for fast installation</li> <li>• High film build in one pass</li> <li>• 100% reactive, no VOCs</li> <li>• Textured anti-slip as-sprayed finish</li> </ul>
<b>Limitations</b>	Not for use beyond its chemical resistance capabilities. Consult ErgonArmor with specific questions.

## INSTALLATION GUIDANCE

<b>Reference Specification</b>	CE-328 Installation Specification for Tufchem Novolac Sprayable Epoxy
<b>Installation Conditions</b>	Materials and substrate should be acclimated to an air temperature of between 50°F (10°C) and 90°F (32°C) during installation and cure.
<b>Mixing/Use</b>	Mix ratio Filler:Resin:Hardener is 6.3:1.0:0.52 by weight. Empty Part A resin and Part B hardener into a clean mixing vessel and mix thoroughly using a slow speed drill with suitable blade mixer such as a Jiffler. Mix for 2 minutes minimum to insure full blending. Slowly add Part C Filler until fully wetted out. Prepare peristaltic pump by lubricating hoses with uncatalyzed resin. Resin can be recovered and reused. Once hoses are wetted out, pour mixed contents into hopper of peristaltic pump and commence spraying.
<b>Work Life</b>	45-60 minutes at 70°F (21°C)
<b>Cleanup</b>	Xylene

## CURE TIME

<b>Temperature</b>	<b>Initial Set</b>	<b>Full Cure</b>
70°F (21°C)	8-12 hours	48 hours

## SAFETY

<b>Safety</b>	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
<b>Ventilation</b>	Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

# Tufchem™ Novolac Sprayable Epoxy

## PACKAGING & ESTIMATING

Product	Code	Packaging
6710 Resin	19592	40 lb/18.1 kg (4.0 gal/15.1 l) pail
6711 Hardener	19595	21 lb/9.5 kg (2.5 gal/9.5 l) pail
Sprayable Epoxy Filler	19706	42 lb (19 kg) bag
<b>Theoretical Coverage</b>	A 313 lb/2.65 cu ft (142 kg/75 l) unit consists of 1 pail of resin, 1 can of hardener and 6 bags of filler and will cover 254 sf (23.6 sm) at 1/8" (3 mm) thickness.	
<b>Storage &amp; Shelf Life</b>	<p>Maintain products in original packaging and sealed until ready for use. Estimated shelf life of components is 18-24 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.</p> <p>If there is any question with respect to the quality of the components check reactivity prior to use. For assistance consult with ErgonArmor.</p>	

## TYPICAL PHYSICAL PROPERTIES

Property	Typical Value
Color	Gray
Wet density	118 lb/ft <sup>3</sup> (1,890 kg/m <sup>3</sup> )
Compressive strength, 1-day, 28-day, ASTM C579	>9,000 psi (62 MPa), >12,000 psi (82.7 MPa)
Tensile strength, 7-day, ASTM C307	>2,000 psi (13.8 MPa)
Flexural strength, ASTM C580	>2,500 psi (17.2 MPa)
Bond to concrete, ASTM C321	Exceeds tensile strength of concrete
Water absorption, ASTM C413	0.3%
Shrinkage, ASTM C531	0.05%
Service temperature range, chemical dependent	180°F (82°C)

**Rev 06/2024**

### TERMS AND CONDITIONS OF SALE

While statements, technical information and recommendations contained herein are based on information our company believes to be reliable, nothing contained herein shall constitute any warranty, express or implied, with respect to the products and/or services described herein and any such warranties are expressly disclaimed. We recommend that the prospective purchaser or user independently determine the suitability of our product(s) for their intended use. No statement, information or recommendation with respect to our products, whether contained herein or otherwise communicated, shall be legally binding upon us unless expressly set forth in a written agreement between us and the purchaser/user. For all Terms and Conditions of Sale see [ergonarmor.com](http://ergonarmor.com).